



The chart above illustrates the ZK6 efficiency when challenged with 50 ppm of hydrogen sulfide. The media performed in excess of 1,300 hours before being expended.

Bulk Density	60 lb/ft ³
Pore Size	4.0 angstroms
Pore Volume	15%
Hardness	5.1 mohs
Impregnant Content	6% w/w (KMnO ₄)

ZK6 presents no health hazard when shipped, stored and handled correctly. Please refer to our Material Safety Data Sheet for more complete information.

This information has been gathered from standard reference materials and/or test procedures and is believed to be true and accurate. It is offered solely for your consideration and verification. None of the information presented shall be construed as constituting a warranty or representation, expressed, written, or implied, for which we assume legal responsibility or that the information or goods described is fit for any particular use either alone or in combination with other goods or processes, or that its use does not conflict with existing patent rights. No license is granted to infringe on any patent rights or practice any patent inversion.